## **MULTIS COMPLEX EP 2**



Lubricating grease



Multi purpose extreme pressure high temperature lithium complex grease.

## **APPLICATIONS**

Multi purpose medium duty EP grease General Lubrication

- MULTIS COMPLEX EP 2 is designed for the lubrication various applications in all types of operating conditions, but particularly where the operation temperature is high and the use of conventional lithium greases is limited.
- MULTIS COMPLEX EP 2 is a true multi purpose grease, formulated for lubrication
  of loaded slide-,ball-, and roller-bearings, wheelbearings, universal joints, chassis,
  and various shock loaded or vibrating applications in transport, agriculture and off
  road vehicles.
- Suitable as general purpose grease for industrial applications requiring a NLGI 2 grade Extreme Pressure grease, resistant to elevated temperatures.
- Always avoid contamination of the grease by dust and/or dirt when applying.
   Preferably use a pneumatic pump system or cartridges.

**SPECIFICATIONS** 

Recommendation

ISO 6743-9: L-XBEHB 2DIN 51502: KP2P-20

## **ADVANTAGES**

Extensive application range
Durable film
Mechanical stability
Thermal stability
Miscible
No harmful substances

- Thanks to its sophisticated formulation MULTIS COMPLEX EP 2 meets a wide variety of requirements. Its range of applications is extensive, allowing stock rationalization and simplification of maintenance.
- Fulfills the requirements of most automotive Original Equipment Manufacturers.
- Forms a lubricating film which is durable, and resistant to humidity, temperature variations and pollution, and hence reduces maintenance and costs.
- Miscible with most other conventional soap greases.
- MULTIS COMPLEX EP 2 does not contain lead, or other heavy metals considered harmful to human health and the environment.

TYPICAL CHARACTERISTICS	METHODES	UNITS	MULTIS COMPLEX EP 2
Soap/thickener		-	Lithium complex
NLGI grade	ASTM D 217/DIN 51 818	-	2
Color	Visual	-	Red
Appearance	Visual	_	Smooth
Operating temperature range		°C	- 20 to 160
Penetration at 25°C	ASTM D 217/DIN51 818	0.1 mm	265-295
Four ball weld load	DIN 51 350-4	daN	280-300
Anti-rust performance SKF- EMCOR	DIN 51 802/IP220/NFT 60-135/ISO 11007	rating	0-0
Dropping point	IP 396/DIN ISO 2176	°C	>275
Kinematic viscosity of the base oil at 40°C	ASTM D 445/DIN 51 562-1/ISO 3104/IP71	mm²/s (cSt)	165

Above characteristics are mean values given as an information.

PT TotalEnergies Marketing Indonesia

1-11-2021

MULTIS COMPLEX EP 2

1/1

This lubricant used as recommended and for the application for which it has been designed does not present any particular risk. A material safety data sheet conforming to the regulations in use in the E.C. is obtainable via your commercial adviser https://ms-sds.totalenergies.com/totalpullwebsite//.

