

# ENS Grease

## Urea-Synthetic High-Temperature Long-Life Grease

**ENS Grease** is a long-life roller bearing grease with excellent properties at both low and high temperatures. It is blended from organic urea thickener, synthetic-ester base oil, and additives that provide outstanding antioxidation performance. **ENS Grease** can be used at high temperatures at which mineral-oil-based greases have very short lives.

### ● Special Features

#### 1. Excellent Heat Resistance

The thickeners in **ENS Grease** are urea compounds, so the grease has a high dropping point and little oil separation. As a result, it has excellent resistance to heat, so it can be used at high temperatures.

#### 2. Outstanding Water Resistance

**ENS Grease** has low water washout, so it is very resistant to water.

#### 3. Superb Rust Prevention

**ENS Grease** contains powerful rust inhibitors, so it prevents rust even in environments exposed to water.

#### 4. Excellent Low-Temperature Properties

**ENS Grease** is blended with synthetic-ester base oil, so it can be used even at temperatures as low as  $-40^{\circ}\text{C}$ .

#### 5. Usable for Long Periods at High Temperatures

Because **ENS Grease**'s synthetic-ester base oil has excellent oxidative stability, this grease can be used for long periods under high-temperature conditions.

### ● Applications

**ENS Grease** is ideal for the following lubrication locations:

- (1) High-speed roller bearings used at low or high temperatures
- (2) Roller bearings in electric-powered machinery
- (3) Roller bearings in electrical components in automobiles
- (4) Roller bearings in drying furnaces
- (5) Roller bearings in blowers
- (6) High-speed roller bearings in machine tools

### ● Containers

180-kg drums and 16-kg pail cans.

### ● Typical Properties of ENS Grease

Thickener				Urea compounds
Base oil				Synthetic-ester oil
Type				31.5
Kinematic viscosity	(40°C)	mm <sup>2</sup> /s		267
Penetration	(25°C, 60 strokes)			310
Worked stability	(25°C, 100,000 strokes)			250 minimum
Dropping point		°C		1.9
Oil separation	(100°C, 24 h)	mass%		0.38
Evaporation	(99°C, 22 h)	mass%		30
Oxidative stability	(99°C, 100 h)	kPa		No change
Copper strip corrosion	(100°C, 24 h)			0.4
Water washout	(79°C, 1 h)	mass%		Level 1 (no rust)
ASTM rust prevention	(52°C, 48 h)			0.15
Low-temperature torque	$-30^{\circ}\text{C}$	N.m		0.02
Starting				2,253
Rotating				
Bearing life	Soda test (6204 bearings, 150°C, 10,000 rpm)	h		

Note: The typical properties may be changed without notice. (June 2002)



## Handling Precautions

▼ Follow these precautions when handling this product.

<b>! CAUTION</b>  <b>Handling Precautions</b>	<ul style="list-style-type: none"><li>● <u>Inflammation can occur if grease enters the eyes.</u> When handling this grease, wear <u>protective goggles</u> or take other measures to <u>prevent eye contact</u>.</li><li>● <u>Inflammation can occur if grease comes into contact with skin.</u> When handling this grease, wear <u>protective gloves</u> or take other measures to <u>prevent skin contact</u>.</li><li>● Do not eat this grease. (Swallowing this grease can cause diarrhea and nausea.)</li><li>● <u>When opening the container, wear protective gloves</u> in order to avoid cutting your hands.</li><li>● <u>Keep out of reach of children.</u></li><li>● Read the Material Safety Data Sheet (MSDS) for this product before using the product. Obtain the Material Safety Data Sheet from where you purchased the product.</li></ul>
<b>First Aid</b>	<ul style="list-style-type: none"><li>● In case of eye contact, rinse eyes thoroughly with clean water and consult with a physician.</li><li>● In case of skin contact, wash skin thoroughly with soap and water.</li><li>● If this grease is swallowed, do not induce vomiting. Consult with a physician immediately.</li></ul>
<b>Disposal of Used Grease and Containers</b>	<ul style="list-style-type: none"><li>● Do not apply pressure to empty containers. The containers may burst if pressure is applied.</li><li>● Do not weld, heat, drill, or cut the containers. The remaining grease may ignite and the containers may explode.</li><li>● Follow all applicable laws and regulations when disposing of used grease or containers. If you are unsure of the proper disposal methods, consult first with the seller of the grease.</li></ul>
<b>Storage Method</b>	Seal the container tightly after use in order to prevent dirt, moisture, etc., from entering the grease. Store in a dark location. Avoid direct sunlight.